

Material List

Precious Alloy

Argident Bio 860Y
Captek
Argident Y73
Argenco 56
Argenco 40
Argident 54
Argident Euro
Argelite 59

Composition

Au 86.5%, Pt 11.0%, Mn 1.0%
Au 84.5%, Pt 5.3%, Pd 7.0%
Au 73.8%, Pt 8.5%, Pd 5.4%
Au 56.0%, Pd 4.11%, Ag 25.0%
Au 40.0%, Pd 4.95%, Ag 45.7%
Au 54.2%, Pd 31.0%, Ag 4.8%
Au 40.3%, Pd 39.4%, Ag 10.0%
Pd 58.9%, Ag 29.0%, In 11.0%

Choice and Supplier

Argen
Captek
Argen
Argen
Argen
Argen
Argen
Argen

FDA 510(K) Approval

K892708
K023831
K892708
K893568
K893413
K891989
K961285
K892813

Non-Precious Alloy

Argeloy NP Supreme

Composition

Co 61.0%, Cr 27.0%, Mo 8.0%

Choice and Supplier

Argen

FDA 510(K) Approval

K935829

Other

EMAX
Empress
Empress
Zirconium
InLine Porcelain Powder
Vita Porcelain Powder
Composite

Composition

Choice and Supplier

IPS e-max® Ceram from Ivoclar
IPS Empress® 2 from Ivoclar
IPS Empress® Esthetic from Ivoclar
IPS e.max® ZirCAD from Ivoclar
IPS InLine® from Ivoclar
Vita
Ceramage from Shofu

FDA 510(K) Approval

K051705
K982616
K913372
K051705
CE 0123
CE 0124
K050401

Partials & Dentures

Chrome Cobalt Framework
Valplast
Denture Bae Polymers
Ivoclar Denture Teeth
Heraeus Kulzer Denture Teeth
COSMO HXL Denture Teeth

Composition

Co 63.2%, Cr 29.3%
N/A
N/A
N/A
N/A
N/A

Choice and Supplier

Wirocast from BEGO
Valplast Int'l
Dentsply Int'l
Ivoclar Liechtenstein
Heraeus Kulzer
Dentsply

FDA 510(K) Approval

K032136
K060507
CELRO0957721/B
K962456 / K844349
K033628
K823744